

# Madras® by Galvolux

## Exclusive decorative glass

### Technical data sheet

### Plissé

**Base product:** patterned glass.

**Description and performance:** the patterned side is chemically satin-finished, opalescent, very smooth to the touch. Effective visual obscuration, optimal light diffusion, fingerprints-resistant.

Lines direction	Lines width	Lines profile
Parallel to 3210 mm side	5 ± 0,15 mm	
Longitudinal pattern deviation tolerance: 3mm/1m.		

**Internal and external applications:** building (façades, parapets...), windows & doors, partitions, furniture, shower-screens etc.

**Plisse can also be supplied in the finishes:**

- Plissé-T - Art. 401240/42 (6/8mm)
- Plissé-M - Art. 401241/37 (6/8 mm)

**Sheet size and thicknesses:**

- Plissé-T/M, 6 mm, 3210 x 2000 mm
- Plissé-T/M, 8 mm, 3210 x 2040 mm

**Maximum possible dimensions:**

- Plissé-T/M, 6 mm, 3160 x 1950 mm
- Plissé-T/M, 8 mm, 3160 x 1990 mm

**Colour:** clear

**Compatible processing:** Cutting, grinding, tempering, varnishing etc.

**Cleaning:** care must be taken when installing the glass not to get putty, resin, sealants, etc., on the treated side. Each of these substances requires a specific solvent for removing traces from glass. For routine maintenance, use water and/or any of the commonly marketed glass detergents. Dry immediately with a clean cloth, preferably micro fibre.



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

## GALVOLUX



QUALITY  
AND WARRANTY  
SINCE 1900

**Galvolux SA**

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com

# Madras® by Galvolux

Exclusive decorative glass

## Plissé

**Defect acceptance limits:** for all defects stemming from production of the base glass, see Standard UNI EN 572-5 (patterned glass).

Acceptance levels for all defects stemming from chemical processing of the glass or as follows:

Defect size/mm	Max no./sheet	average per 20 m <sup>2</sup>
>0,6 e > 1,5	3	5
>1,5 e > 3,0	1	2
>3,0 e > 9,0	only with customer acceptance	only with customer acceptance



Colours and finishings in the photographs may look slightly different from those of the real products: we recommend that customers examine sample glass before choosing products.

**GALVOLUX**



QUALITY  
AND WARRANTY  
SINCE 1900

**Galvolux SA**

Via Strecce 1 - CH 6934 Bioggio

Tel. +41 91 610 55 11

info@galvolux.com

www.galvolux.com